

Sonnenschutz



***SOLTIS*[®] LowE**

Soltis 99


www.ferrari-architecture.com

FERRARI
architecture




SOLTIS 99


ALU

	composition	polyester / pvc
	weight [g/m2]	290
	thickness	0.32
	fire classification	M1
	ultraviolet test UV	5/5
	openness factor [%]	3
	Ts [%]	5
	Rs [%]	45
	As [%]	50
	Tv [%]	12
	application	int


ANTRACITE

	composition	polyester / pvc
	weight [g/m2]	290
	thickness	0.32
	fire classification	M1
	ultraviolet test UV	5/5
	openness factor [%]	3
	Ts [%]	3
	Rs [%]	36-9
	As [%]	61-88
	Tv [%]	2
	application	int


LIGHT GRAY

	composition	polyester / pvc
	weight [g/m2]	290
	thickness	0.32
	fire classification	M1
	ultraviolet test UV	5/5
	openness factor [%]	3
	Ts [%]	7
	Rs [%]	47-45
	As [%]	46-48
	Tv [%]	6
	application	int


QUARTZ

	composition	polyester / pvc
	weight [g/m2]	290
	thickness	0.32
	fire classification	M1
	ultraviolet test UV	5/5
	openness factor [%]	3
	Ts [%]	9
	Rs [%]	47-60
	As [%]	44-31
	Tv [%]	8
	application	int


SANDY BEIGE

	composition	polyester / pvc
	weight [g/m2]	290
	thickness	0.32
	fire classification	M1
	ultraviolet test UV	5/5
	openness factor [%]	3
	Ts [%]	7
	Rs [%]	44-45
	As [%]	49-48
	Tv [%]	6
	application	int

SPUME

	composition	polyester / pvc
	weight [g/m2]	290
	thickness	0.32
	fire classification	M1
	ultraviolet test UV	5/5
	openness factor [%]	3
	Ts [%]	9
	Rs [%]	48-63
	As [%]	43-28
	Tv [%]	7
	application	int

WHITE

	composition	polyester / pvc
	weight [g/m2]	290
	thickness	0.32
	fire classification	M1
	ultraviolet test UV	5/5
	openness factor [%]	3
	Ts [%]	9
	Rs [%]	50-69
	As [%]	41-22
	Tv [%]	8
	application	int